

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Consommation
et Corporations Canada

Consumer and
Corporate Affairs Canada

Bureau des brevets

Patent Office

Ottawa, Canada
K1A 0C9

(21)	(A1)	2,018,591
(22)		1990/06/08
(43)		1991/12/08
(52)		305-39

5,005,9/23

(51) INTL.CL.⁵ B62B-17/02

(19) (CA) **APPLICATION FOR CANADIAN PATENT** (12)

(54) High Speed Ski

(72) Jacques, Michel - Canada ;

(73) Bombardier Inc. - Canada ;

(57) 19 Claims

Notice: The specification contained herein as filed

Canada

CCA 3254 (10-89) 41

ABSTRACT

A snowmobile ski is made of two main parts, namely a steel stiffener and a sole made of ultra high molecular weight polyethylene (UHMW-PE) to which a friction reducing additive has been added. The front handle is molded integrally with the ski sole and then bent back and secured to the sole and stiffener. The sole has upstanding projections on which the stiffener rests so that spaces are provided which allow the sole to deflect when impacted thereby reducing transmission of impacts to the stiffener. The stiffener is formed with a main stiffener and secondary stiffeners provided only when the ski is to be attached to the suspension assembly. The secondary stiffeners coact with the main stiffener to increase the strength and rigidity while minimizing the weight increase.

This invention relates to snowmobile skis.

Traditionally all snowmobile skis have been made of steel. A backbone is welded to the sole to form a closed box or an open U-shape.

Some skis, not for snowmobiles, have been made of reinforced plastics, plastics and wood or a combination of these materials.

10 Recently a snowmobile ski has been proposed by Ultimate Sports Inc. in which the ski is made of two main parts, namely a cast aluminum backbone or stiffener and a sole made of ultra high molecular weight-polyethylene (UHMW-PE). According to this design characteristics such as the static and dynamic coefficients of friction, dynamic stability and turning response of the ski can be determined by choice of material of the sole and profile of the sole, while characteristics such as ability to withstand static and dynamic loads are determined by design of the stiffener. By separating out these two different sets of parameters the ski design can be optimized.

20 The ski proposed by Ultimate suffers from the following disadvantages. Firstly, the bottom of the stiffener is flat and it rests on top of a flat upper surface of the sole. Thus, impacts on the sole are transmitted directly through to the stiffener which would have the effect of weakening the stiffener.

Secondly, when the ski is to be mounted to a suspension assembly of the snowmobile, the stiffener is thickened to increase the strength and rigidity at that point. However, the increase in thickness greatly increases the overall weight of the ski which is

undesirable.

Thirdly, the UHMW-PE used in the sole is subject to wear.

Fourthly, the front handle of the ski is formed of a separate component, adding to manufacturing and assembly costs.

Fifthly, the use of cast aluminum for the main stiffener is more expensive compared to the use of a steel stiffener.

It is an object of the present invention to obviate or mitigate one or more of these disadvantages.

10 This is achieved, according to one aspect of the present invention, by providing a ski for a snowmobile, the ski having an upwardly curved forward end and comprising a sole made of a plastics material, a runner at the underside of the sole and a rigid metal stiffener on top of the sole and means securing the runner, sole and stiffener together wherein the sole is provided with upstanding projections on which the stiffener rests, spaces between the projections allowing the sole to deflect when impacted thereby reducing transmission of impacts to the stiffener.

20 In a preferred embodiment the projections are formed of spaced ribs extending along the sole.

According to another aspect of the invention an effect similar to that achieved by thickening the stiffener at the location where the ski is to be attached to the suspension assembly is achieved by providing instead secondary stiffener members only at that location. The secondary stiffener members coact with the main stiffener and increase the strength and rigidity while minimizing the weight increase.

According to a further aspect of the invention, additives such as organic peroxides and/or glass microspheres are added to the UHMW-PE to increase wear resistance of the sole.

10 In another aspect of the invention, the front handle is integrally formed with the ski sole in the one molding process after which the handle is bent back and secured to the sole and stiffener. This allows the use of only one tool to fabricate the handle and the ski sole and simplifies assembly. Another result is a reduction in weight. It also allows the front end of the ski to be flexible and thus to take high impacts without damaging the ski.

The use of steel instead of cast aluminum as the material in a preferred embodiment of the invention reduces the cost.

The invention will now be described in greater detail with reference to the accompanying drawings, in which:

Figure 1 is a perspective view of a new ski constructed according to the invention;

Figure 2 is an exploded perspective view of the ski of Figure 1;

20 Figure 3 is a sectional view taken on A-A of Figure 1;

Figure 4 is a sectional view taken on B-B of Figure 1;

Figure 5 is a perspective view of the ski sole used in the ski of Figures 1 to 4, illustrating detailed features of the sole;

Figure 6 is a side view of the ski sole of Figure 5;
and

Figure 7 is a sideview of the ski sole after molding but

before bending into final shape.

Referring to the drawings, a ski 10 is formed of two principal parts, namely a backbone or stiffener 12 and a sole 14. The stiffener 12 is made of metal such as stamped steel coated with powder epoxy to protect it against corrosion and wear. Other metals such as aluminum magnesium also could be used. The sole 14 is made of plastic material, a preferred material being ultra high molecular weight-polyethylene (UHMW-PE) to which an additive to improve wear resistance has been added. Different additives e.g. organic peroxide and glass microspheres can be used for this purpose but the inventors have determined in tests that an organic peroxide in conjunction with glass microspheres in an amount of approximately 5% by weight as additive gives good results for a snowmobile ski sole and also that the use of these additives separately gives good results.

As seen in Figures 2 and 3 a steel runner 16 forms a third component of the ski. The runner 16 is accommodated partly in a recess 18 extending lengthwise along the underside of the sole 14, as seen particularly in Figure 3. The runner has up-standing integral stud portions 20 provided at spaced locations along the runner. The stud portions 20, which are threaded at their free ends, are received through holes 22 in the sole 14 and aligned holes 24 in the stiffener 12. Lock nuts 26 received in the threaded ends of the stud portions 20 secure the runner, sole and stiffener together.

Details of the structure of sole 14 are seen most clearly in Figures 3, 4 and 5. The sole 14 is elongate with an

upwardly curved forward end 28, from the leading end of which extends an integrally formed handle 30 that is bent back into engagement with the upper surface 32 of the sole, and a slightly upwardly sloping rear end 34.

The handle 30 has a free end portion 36 which is con-
formed generally in shape to the shape of the curved forward end
28 of the sole and has therein a through hole 38 which is aligned
with a through hole 40 (Figure 6) in the sole. As seen in Figures
1 and 2, a bolt 42 is received through the hole 40 in sole 14,
10 then through an aligned hole 24 in stiffener 12 and finally
through hole 38 in handle 30. A nut 44 secures the free end 36 of
the handle to the stiffener 12.

As seen in Figures 3 and 4, in section the sole 14 has
two generally flat, horizontal marginal portions 46 extending most
of the length of the sole and into the curved forward end 28. The
inner sides of the marginal portion 46 are bonded by respective
upstanding ribs 48 running lengthwise along the sole. The central
portion 50 of the sole located between the two ribs 48 is formed
generally as a shallow U along the lower surface of which runs the
20 recess 18 for receiving the runner 16. From the upper surface of
the central position extend three vertical spaced ribs 52
extending lengthwise along the sole. At the locations of the
holes 22 and 40 the ribs merge to form flat platforms 54.
Outwardly of the ribs 52 the upper surface of the central portion
of the sole 14 is formed with two flat, horizontal margins 55
located adjacent the ribs 48. As seen in Figures 1, 2 and 5 a
transverse rib 56 is located at a short spacing from the rear end

of the sole, rib 56 extending between ribs 48.

The stiffener 12 is formed of a main stiffener member 58 and two secondary stiffeners 60. The main stiffener 58 is generally channel shaped, having two upstanding sides 61 joined by a bottom 62. The bottom 62 has two horizontal marginal portions 64 and a central depressed portion 66 joined to the marginal portions 64 by means of sloping portions 68. In the longitudinal direction the bottom 62 of this stiffener 58 curves upwardly at the forward portion of the stiffener to conform to the shape of the sole. The sides 61 of stiffener 58 have inturned horizontal flanges 69 at their free ends. The sides 61 are provided with some elongate through holes 70 which, as seen in Figure 4, have inturned stiffening flanges 72. The holes are provided to reduce weight and the flanges 72 are provided to increase the resistance to flexure. Also provided in sides 61 are aligned round holes 74 which, as seen in Figure 3, receive steel bushings 76.

The bushings 76 also pass through aligned holes 78 in the secondary stiffeners 60, which are identical to each other and each of which is formed as a plate having horizontal bottom edge and a top edge which is shaped like a shallow inverted V and which has an outturned flange 80.

As seen in Figure 3, the secondary stiffeners 60 are welded to the respective main stiffeners 58 where the flanges 80 engage the sides 61 and where the bottom edges engage the marginal portions 64 of the bottom 62. The secondary stiffeners are also welded to the respective bushings 76. In use, a pivot pin (not shown) is received through the bushings 76 for pivotal connection

of the ski 10 to an appropriate suspension assembly of the snowmobile.

As seen in Figure 3, the stiffener 12 is received with slight clearance between the two ribs 48 of sole 14 with the bottom 62 of the main stiffener resting on portions of the sole located between the two ribs 48. More particularly, the central depressed portion 66 of the bottom rests on the tops of the three vertical ribs 52 with the marginal portions 64 of the bottom resting on the margins 55. The transverse rib 56 serves, as seen
10 in Figure 1, as a stop for the rear edge of stiffener 58.

In manufacturing the sole a compression molding process is used resulting in the molded sole shape shown in Figure 7 in which the handle 30 extends away from the sole 14 and generally parallel to the major portion of the sole. When assembling the stiffener 12 to sole 14 the handle 30 is simply bent back by hand and secured by the nut and bolt as explained above.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE
PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A ski for a snowmobile, the ski having an upwardly curved forward end and comprising a sole made of a plastics material, a runner at the underside of the sole and a rigid metal stiffener on top of the sole and means securing the runner, sole and stiffener together, wherein the forward end of the sole is integrally formed with an elongate strip which is bent back and secured at a free end to the sole and stiffener thereby forming a handle.
2. A ski according to claim 1 wherein the free end of the elongate strip is secured between the sole and the stiffener.
3. A ski according to claim 2 wherein the free end of the elongate strip is provided with a through hole which is aligned with through holes in the sole and the stiffener and a bolt is received through the aligned holes and is mounted with a nut.
4. A ski according to claim 1, 2 or 3 wherein the sole and handle are made of UHMW-PE.
5. A ski according to claim 4 wherein at least one of an organic peroxide and glass microspheres has been added to the UHMW-PE.
6. A ski for a snowmobile, the ski having an upwardly

curved forward end and comprising a sole made of a plastics material, a runner at the underside of the sole and a rigid metal stiffener on top of the sole and means securing the runner, sole and stiffener together wherein the sole is provided with upstanding projections on which the stiffener rests, spaces between the projections allowing the sole to deflect when impacted thereby reducing transmission of impacts to the stiffener.

7. A ski according to claim 6 in which the projections are formed as a plurality of spaced ribs extending lengthwise of the sole.

8. A ski according to claim 6 or 7 wherein the sole is made of UHMW-PW.

9. A ski according to claim 8 wherein at least one of an organic peroxide and glass microspheres has been added to the UHMW-PE.

10. A ski for a snowmobile, the ski having an upwardly curved forward end and comprising a sole made of a plastics material, a runner at the underside of the sole and a rigid metal stiffener on top of the sole and means securing the runner, sole and stiffener together, in which the stiffener is formed of a main stiffener member formed generally as a channel extending along a major portion of the sole length, the channel having two spaced sides and a bottom, and two secondary stiffener members secured to

the main stiffener member, the secondary stiffener members being provided at a pivot location at which the ski is to be mounted to a suspension assembly, the secondary stiffener members each having a plate portion extending over the pivot location and spaced from a respective one of the channel sides and having a portion abutting the respective channel side whereby the stiffener is effectively strengthened at the pivot location.

11. A ski according to claim 10, wherein the abutting portion of each secondary stiffener member is a right angled flange provided at an upper edge of the plate portion, a lower edge of the plate portion rests on the bottom of the main stiffener member and the secondary stiffener members are welded to the main stiffener member at the flanges and the lower edges.

12. A ski according to claim 10 or 11 in which the main stiffener member is provided with through holes to decrease its weight, each through hole being turned in at its edge to form a stiffening flange.

13. A ski according to claim 10 or 11 wherein two aligned bushings are provided at the pivot location, one bushing extending through one of the secondary stiffener members and one side of the main stiffener member and the other bushing extending through the other secondary stiffener and the other side of the main stiffener member.

14. A ski for a snowmobile, the ski having an upwardly curved forward end and comprising a sole made of a plastics material, a runner at the underside of the sole and a rigid metal stiffener on top of the sole and means securing the runner, sole and stiffener together, wherein the sole is made of UHMW-PE to which an additive to improve wear resistance has been added.
15. A ski according to claim 14 wherein the additive is at least one of an organic peroxide and glass microspheres.
16. A ski according to claim 15 wherein the amount of additive is approximately 5% by weight.
17. A ski for a snowmobile, the ski having an upwardly curved forward end and comprising a sole made of a plastics material, a runner at the underside of the sole and a rigid metal stiffener on top of the sole and means securing the runner, sole and stiffener together wherein the sole is provided with upstanding projections on which the stiffener rests, spaces between the projections allowing the sole to deflect when impacted thereby reducing transmission of impacts to the stiffener and wherein the stiffener is formed of a main stiffener member formed generally as a channel extending along a major portion of the sole length, the channel having two spaced sides and a bottom, and two secondary stiffener members secured to the main stiffener member, the secondary stiffener members being provided at a pivot location at which the ski is to be mounted to a suspension assembly, the


secondary stiffener members each having a plate portion extending over the pivot location and spaced from a respective one of the channel sides and having a portion abutting the respective channel side whereby the stiffener is effectively strengthened at the pivot location.

18. A ski according to claim 17 wherein the forward end of the sole is integrally formed with an elongate strip which is bent back and secured at a free end to the sole and stiffener thereby forming a handle.

19. A ski according to claim 18 wherein the sole and handle are made of UHMW-PE to which at least one of an organic peroxide and glass microspheres has been added.

SMART & BIGGAR
OTTAWA, CANADA

PATENT AGENTS



Patent Agents
Smart & Big...

FIG. 3







FIG. 4

Patent Agents
Smart & Biggar



Patent Agents.
Smart & Biggar



*Patent Agents
Smart & Biggar*